

Floorsafe Australia Pty Ltd

Slip Resistance of Fibreglass Stair Nosing - Normal

Fibreglass Stair Nosing - Normal		
AS 4586:2013 ¹		Suitable for locations that include: ^{2 3}
Classification	Slip Resistance Value - SRV	
P5	71 (69 – 73)	<ul style="list-style-type: none"> • External Ramps including sloping driveways, footpaths etc., steeper than 1 in 14 • External sales areas, external carpark areas, external colonnades, walkways, pedestrian crossings, balconies, verandas, carports, driveways, courtyards, and roof decks. • Loading docks undercover and commercial kitchens • Swimming pool ramps and stairs leading to water • Undercover concourse areas • Entries and access areas including hotels offices, public buildings, schools kindergartens, common areas of public buildings, internal lift lobbies – WET⁴ areas • Shop entry areas with external entrances

Our reference: FLO0315-1
Investigating officer: Kate Tonkin
Issue Date: 24 April 2015

James P Mann
 Laboratory Manager



¹ Slip resistance was determined in accordance with Appendix A of AS 4586:2013 “Slip resistance classification of new pedestrian surface materials” using a Slider 96 (4S) rubber slider.

² According to Table 3B of the Standards Australia Handbook HB198:2014 – “Guide to the specification and testing of slip resistance of pedestrian surfaces”

³ 5.2 of HB198 states: “The use of these values should be in the context of design, which also considers abnormal wear, maintenance, abnormal contamination, the presence (or otherwise) of water or other lubricants, the nature of the pedestrian traffic (including age, gait and crowding), the footwear (or lack thereof), slope lighting and handrails.”

⁴ According to HB198, *Wet areas* are, “...those areas that are not defined as a dry or transitional area, which may be either constantly or intermittently wet or otherwise contaminated.”

Stone Initiatives shall not be liable for loss, cost, damage or expense incurred by the client, or any other person or company, resulting from the use of any information or interpretation given in this report. The results relate only to the items tested.



WET SLIP RESISTANCE (AS 4586:2013 APP A) Test Certificate

TEST METHOD	AS 4586:2013 Appendix A (Wet Pendulum)		
TEST DATE	17-Apr-15		
CLIENT	Floorsafe Australia Pty Ltd		
OUR REFERENCE	FLO0315-1		
SAMPLE	Fibreglass stair nosing - FG1 (Normal)		
SURFACE FINISH	Fibreglass texture		
SAMPLE ORIGIN	Floorsafe Australia		
SAMPLING DATE	1/03/2015	SAMPLE LOCATION	Not Known
NOMINAL SIZE	70x600x3 mm		
AIR TEMPERATURE	20.0 °C	TEST SITE	SI Laboratory
WEATHER	Not Applicable		
TEST TYPE	Unfixed		
ANGLE OF TEST	Horizontal		
SLIDER TYPE	Slider 96	SLIDER EXPIRY	17-Oct-15
SLIDER PREPARATION	Slider passed 3x over 400 grit paper, 10x over 3mic lapping film.		
SURFACE PREPARATION	Washed with potable water and cloth		

Test Number	Orientation	BPN Readings	Mean
S8255	O421/1 Random	69, 72, 68, 69, 69	69
S8256	O421/2 Random	69, 71, 71, 72, 71	71
S8257	O421/3 Random	67, 74, 71, 72, 69	71
S8258	O421/4 Random	69, 74, 71, 74, 74	73
S8259	O421/5 Random	71, 69, 69, 71, 70	70

MEAN Wet SLIP RESISTANCE VALUE (SRV): 71 ±2 (u95)
SLIP RESISTANCE CLASSIFICATION: P5


NOTE: The expanded measurement uncertainty values (u95) quoted in this report are at a confidence level of 95 % with a nominal coverage factor of 2. These values do not include any estimate of the effects associated with sampling.

COMMENTS/VARIATION

TESTED BY: Kate Tonkin

APPROVED SIGNATORY:

NAME: James P Mann



ISSUE DATE: 23-Apr-15



This report shall not be reproduced except in full without written approval of Stone Initiatives. Results relate only to the items tested.

Accredited for compliance with ISO/IEC 17025.

The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards.

Stone Initiatives and Materials Testing Group Pty Ltd
2/19 Light Crescent, Mount Barker SA 5251
www.stonemtg.com.au

ABN 82 462 051 744 | ACN 106 166 296
P +61 (0) 8 8391 6844
info@stonemtg.com.au