



Floorsafe Australia Pty Ltd

Slip Resistance of Franklin Stair Nosing Range

Franklin Stair Nosing Range		
AS 4586:2013 ¹		
Classification	Slip Resistance Value - SRV	Suitable for locations that include: ^{2 3}
P5	85 (73 – 98)	 External Ramps including sloping driveways, footpaths etc., steeper than 1 in 14 External sales areas, external carpark areas, external colonnades, walkways, pedestrian crossings, balconies, verandas, carports, driveways, courtyards, and roof decks. Loading docks undercover and commercial kitchens Swimming pool ramps and stairs leading to water Undercover concourse areas Entries and access areas including hotels offices, public buildings, schools kindergartens, common areas of public buildings, internal lift lobbies – WET⁴ areas Shop entry areas with external entrances

Our reference: FLO0315-1
Investigating officer: Kate Tonkin
Issue Date: 24 April 2015

James P Mann Laboratory Manager

Stone Initiatives shall not be liable for loss, cost, damage or expense incurred by the client, or any other person or company, resulting from the use of any information or interpretation given in this report. The results relate only to the items tested.

¹ Slip resistance was determined in accordance with Appendix A of AS 4586:2013 "Slip resistance classification of new pedestrian surface materials" using a Slider 96 (4S) rubber slider.

² According to Table 3B of the Standards Australia Handbook HB198:2014 – "Guide to the specification and testing of slip resistance of pedestrian surfaces"

⁵ 5.2 of HB198 states: "The use of these values should be in the context of design, which also considers abnormal wear, maintenance, abnormal contamination, the presence (or otherwise) of water or other lubricants, the nature of the pedestrian traffic (including age, gait and crowding), the footwear (or lack thereof), slope lighting and handrails."

⁴ According to HB198, *Wet areas* are, "...those areas that are not defined as a dry or transitional area, which may be either constantly or intermittently wet or otherwise contaminated."







WET SLIP RESISTANCE (AS 4586:2013 APP A) Test Certificate

TEST METHOD AS 4586:2013 Appendix A (Wet Pendulum)

TEST DATE 17-Apr-15

CLIENT Floorsafe Australia Pty Ltd

OUR REFERENCE FLO0315-1

SAMPLE Franklin stair nosing range - RC20

SURFACE FINISH 5mm anodised aluminium with 12mm carborundum strips

SAMPLE ORIGIN Floorsafe Australia

SAMPLING DATE 1/03/2015 SAMPLE LOCATION Not Known

NOMINAL SIZE 50x600x5 mm

AIR TEMPERATURE 20.0 ° C TEST SITE SI Laboratory

WEATHER Not Applicable
TEST TYPE Unfixed
ANGLE OF TEST Horizontal
SLIDER TYPE Slider 96 SLIDER EXPIRY 17-Oct-15

SLIDER PREPARATION Slider passed 3x over 400 grit paper, 10x over 3mic lapping film.

SURFACE PREPARATION Washed with potable water and cloth

Test Orientation **BPN Readings** Mean Number S8265 O422/1 Random 99, 95, 98, 99, 96 98 S8266 O422/2 Random 105, 80, 96, 81, 93 90 78, 90, 83, 89, 84 S8267 O422/3 Random 85 S8268 86, 74, 74, 80, 84 79 O422/4 Random S8269 O422/5 Random 74, 75, 78, 72, 74, 72 73

MEAN Wet SLIP RESISTANCE VALUE (SRV): 85 ±2 (U95)

SLIP RESISTANCE CLASSIFICATION: P5

NOTE: The expanded measurement uncertainty values (u95) quoted in this report are at a confidence level of 95 % with a nominal coverage factor of 2. These values do not include any estimate of the effects associated with sampling.

COMMENTS/VARIATION results recorded are a representative of an erratic range of readings from X to X.

TESTED BY: Kate Tonkin
APPROVED SIGNATORY:
NAME: James P Mann

ISSUE DATE: 23-Apr-15

This report shall not be reproduced except in full without written approval of Stone Initiatives. Results relate only to the items tested.

Stone Initiatives and Materials Testing Group Pty Ltd 2/19 Light Crescent, Mount Barker SA 5251 www.stonemtg.com.au

ABN 82 462 051 744 | ACN 106 166 296 P +61 (0) 8 8391 6844 info@stonemtg.com.au