

**50mm Carborundum Insert – Carb Insert Black**

	Average LRVs	
	DRY	WET
TRISTIMULUS COLORIMETER	5.20	3.02
SPECTROPHOTOMETER	5.63	1.50
<b>Combined Average LRV</b>	<b>5.41</b>	<b>2.26</b>

**Hazardous Fibreglass Stair Nosing - FGHZ**

	Average LRVs	
	DRY	WET
TRISTIMULUS COLORIMETER	39.33	34.15
SPECTROPHOTOMETER	34.55	24.47
<b>Combined Average LRV</b>	<b>36.94</b>	<b>29.31</b>

**Polyurethane Tactile Pads – T20 Grey**

	Average LRVs	
	DRY	WET
TRISTIMULUS COLORIMETER	15.93	14.12
SPECTROPHOTOMETER	18.27	16.48
<b>Combined Average LRV</b>	<b>17.10</b>	<b>15.30</b>

## 6. Conclusion

Luminos Consulting has performed the luminance reflectance value (LRV) tests as prescribed in the abovementioned methodologies for the provided product samples, and conclude that the results indicate the subject product samples to have the following LRV:

- |              |                                  |               |                                  |
|--------------|----------------------------------|---------------|----------------------------------|
| • T10 White  | – 69.66 in dry<br>– 65.79 in wet | • T10 T-Cotta | –11.14 in dry<br>– 11.96 in wet  |
| • T20 Yellow | – 37.44 in dry<br>– 35.11 in wet | • T10 Grey    | – 15.53 in dry<br>– 15.79 in wet |
| • T20 Ivory  | – 55.05 in dry<br>– 48.85 in wet | • T09 Blue    | – 7.86 in dry<br>– 7.28 in wet   |
| • T20 Black  | – 55.05 in dry<br>– 48.85 in wet | • RNM Black   | – 5.88 in dry<br>– 3.95 in wet   |
| • T25        | – 14.41 in dry<br>– 2.69 in wet  | • SN60 Grey   | – 15.11 in dry<br>– 16.33 in wet |
| • T01        | – 36.67 in dry<br>– 24.40 in wet | • FG Yellow   | – 33.12 in dry<br>– 24.76 in wet |
| • T05 Black  | – 2.79 in dry<br>– 2.12 in wet   | • SN60 Black  | – 2.87 in dry<br>– 1.88 in wet   |
| • T10 Yellow | – 34.53 in dry<br>– 33.60 in wet | • SN60 Yellow | – 47.15 in dry<br>– 43.97 in wet |

- |                        |                                  |  |                                  |
|------------------------|----------------------------------|--|----------------------------------|
| • T09 Terr             | - 13.11 in dry<br>- 12.57in wet  | • T09 White                                | - 69.35 in dry<br>- 55.02 in wet |
| • T03                  | - 58.19 in dry<br>- 51.47in wet  | • Carb Insert Grey                         | - 21.11 in dry<br>- 17.43 in wet |
| • T20 Black            | - 3.01 in dry<br>-1.00 in wet    | • FG Black                                 | - 5.41 in dry<br>- 3.81 in wet   |
| • Carb Insert Yellow   | - 41.79 in dry<br>- 35.17 in wet | • T09 Grey                                 | - 16.40 in dry<br>- 17.29 in wet |
| • Rubber Insert Black  | - 3.36 in dry<br>- 3.91 in wet   | • T22                                      | - 2.32 in dry<br>- 1.61 in wet   |
| • Rubber Insert Grey   | - 17.81 in dry<br>- 16.53 in wet | • T09 Black                                | - 5.87 in dry<br>- 2.08 in wet   |
| • RST50                | - 53.80 in dry<br>- 49.77 in wet | • Luminous Insert – 3 Glow Luminous Insert | - 10.47 in dry<br>- 10.44 in wet |
| • RST50 BLACK          | - 3.34 in dry<br>- 1.96 in wet   | • Tape – Anti slip tape – Yellow           | - 51.25 in dry<br>- 47.64 in wet |
| • T20 Terr             | - 14.53 in dry<br>- 12.95 in wet | • Tape – Anti slip tape – Black            | - 3.16 in dry<br>- 1.29 in wet   |
| • Rubber Insert Yellow | - 48.01 in dry<br>- 42.06in wet  | • T20 Blue                                 | - 8.63 in dry<br>- 7.78 in wet   |
| • RNS                  | - 62.96 in dry<br>- 53.41in wet  | • Carb Insert Black                        | - 5.41 in dry<br>- 2.26 in wet   |
| • RNM Yellow           | - 40.52 in dry<br>- 31.92 in wet | • FGHZ                                     | - 36.94 in dry<br>- 29.31 in wet |
| • T05 Yellow           | - 31.86 in dry<br>- 27.38 in wet | • T20 Grey                                 | - 17.10 in dry<br>- 15.30 in wet |

Should you require anything further or clarification of anything contained herein please feel free to contact us on 1300 852 642 or via email on [office@luminos.com.au](mailto:office@luminos.com.au).

Yours faithfully,  
**LUMINOS CONSULTING**



PAUL MULHOLLAND  
Disability Access Consultant  
*Association of Consultants in Access Australia Inc.*  
*Membership No. Pending*



BRUCE BROMLEY  
Disability Access & Egress Consultant  
*Association of Consultants in Access Australia Inc.*  
*Accredited Membership No. 187*